



PSPR



PSPSR



Type	材質	硬度
PSPR	彈簧用鋼	45~50HRC
PSPSR	不銹鋼彈簧用鋼	42~48HRC

L	L尺寸公差
5~10	+0.5 0
12~50	+1.0 0
56~100	+1.5 0

Type	品號		*kN		t(參考)		D	
	D - L		PSPR	PSPSR	PSPR	PSPSR	min	max
PSPR (D2~10)	2	參考 下表	2.76	2.76	0.4	0.4	2.15	2.25
			6.2	6.2	0.6	0.6	3.15	3.25
			10.8	10.8	0.8	0.8	4.2	4.4
			17.25	17.25	1.0	1.0	5.2	5.4
PSPSR (D2~6)	6	參考 下表	24.83	24.83	1.2	1.2	6.2	6.4
			44.13	-	1.6	-	8.3	8.6
			68.94	-	2.0	-	10.3	10.6

Wa) 注意

- D的最大值是銷圓周上的最大值，D的最小值是D₁、D₂、D₃的平均值
- 參考t的數值是依據JSMA No.6(日本彈簧工業會規格)
- * kN=雙重剪斷荷重最小值

Type	品號		庫存	
	D-L	PSPR	PSPSR	
PSPR (鋼)	2-5			
	6	·		
	8		·	
	10			·
	12			
	14	·		
	16			·
	18			·
	20			
	22			
PSPSR (不銹鋼)	3-6			
	8			·
	10			·
	12	·		
	14			
	16			·
	18			·
	20			
	22			
	25	·		·
PSPR (鋼)	4-8			
	10			·
	12			
	14			
	16	·		
	18			
	20			
	22			
	25			·
	28			
PSPR (鋼)	32			
	36	·		
	40			
	40			

Type	品號		庫存	
	D-L	PSPR	PSPSR	
PSPR (鋼)	5-10			
	12			
	14			
	16	·		·
	18			
	20			
	22			
	25			
	28	·		
	32			·
PSPSR (不銹鋼)	36			
	40			
	45	·		·
	50			
	6-12			
	14			
	16	·		·
	18			
	20			
	22			
PSPR (鋼)	25			
	28			
	32	·		·
	36			
	40			
	45			
	50	·		·
	56			
	8-16			·
	18			
PSPR (鋼)	20			·
	22			
	25			
PSPR (鋼)	28			·
	28			

Type	品號		庫存	
	D-L	PSPR	PSPSR	
PSPR (鋼)	8-32	·		
	36	·		
	40	·		
	45			
	50	·		
	56	·		
	63	·		
	70	·		
	80	·		
	80	·		
PSPR (鋼)	10-18	·		
	20	·		
	22	·		
	25	·		
	28	·		
	32	·		
	36	·		
	40	·		
	45	·		
	50	·		
PSPSR (不銹鋼)	56	·		·
	63	·		
	70	·		
	80	·		
	90	·		
	100	·		

訂貨： 交期：

PSPR2-5