



D mm	真圓度 μm
<13	0.004
<20	0.005
<30	0.006

TYPE	公差	材質	熱處理	硬度	表面處理	備註
GKS002-A	g6	SUJ2	高週波	HRC58	-	適用於配合線性襯套 (請參閱線性襯套· 小型滾珠導件單元)
GKS002-B		SUS440C		HRC56		
GKS002-C		SUJ2		HRC58		
GKS002-D		SUS440C		HRC56		
CRS.B	f8	S45C	-	-	硬鉻	適用於配合自潤軸承 (請參閱自潤軸承單元)
SUSC.B	f8	SUS304	-	-	-	

D mm	淬火深度 (mm)	
	SUJ2	SUS440C
<10	0.5	0.5
<13	0.7	0.5
<20	0.7	0.7
<25	1.0	0.7

L mm	公差 mm
<6	±0.1
<30	±0.2
<120	±0.3
<400	±0.5
<1000	±0.8
<1500	±1.2

品號		g6公差 mm	f8公差 mm	L 指定單位1mm	D1	D1 公差	L1	L1 公差	L2	C	
TYPE	D										
(g6)	GKS002-A	3	-0.002 -0.008	-0.006 -0.020	10~400	2	+0.06 0	0.5	+0.05 0	2	0.5
	GKS002-B	4	-0.004 -0.012	-0.010 -0.028	10~400	3	+0.06 0	0.7	+0.1 0	2	0.5
	GKS002-C	5	-0.004 -0.012	-0.010 -0.028	10~400	4	+0.075 0	0.7	+0.1 0	2	0.5
	GKS002-D	6	-0.004 -0.012	-0.010 -0.028	20~600	5	+0.075 0	0.7	+0.1 0	2	0.5
	GKS002-A	8	-0.005 -0.014	-0.013 -0.035	20~800	7	+0.09 0	0.9	+0.1 0	3	0.5
	GKS002-B	10	-0.005 -0.014	-0.013 -0.035	20~800	9.6	0 -0.09	1.15	+0.14 0	3	0.5
(f8)	GKS002-C	12	-0.006 -0.017	-0.016 -0.043	20~1000	11.5	0 -0.11	1.15	+0.14 0	4	0.5
	GKS002-D	13	-0.006 -0.017	-0.016 -0.043	25~1000	12.4	0 -0.11	1.15	+0.14 0	4	0.5
	CRS.B	15	-0.006 -0.017	-0.016 -0.043	25~1000	14.3	0 -0.11	1.15	+0.14 0	4	0.5
	SUSC.B	16	-0.006 -0.017	-0.016 -0.043	30~1200	15.2	0 -0.11	1.15	+0.14 0	4	0.5
	SUSC.B	18	-0.006 -0.017	-0.016 -0.043	30~1200	17	0 -0.11	1.35	+0.14 0	4	0.5
	SUSC.B	20	-0.007 -0.020	-0.020 -0.053	30~1200	19	0 -0.21	1.35	+0.14 0	4	1.0
	SUSC.B	25	-0.007 -0.020	-0.020 -0.053	35~1200	23.9	0 -0.21	1.35	+0.14 0	5	1.0
SUSC.B	30	-0.007 -0.020	-0.020 -0.053	35~1500	28.6	0 -0.21	1.65	+0.14 0	5	1.0	

【PS】備註

· CRS.B和SUSC.B的外徑公差是f8，未熱處理

訂貨： TYPE [ ] D [ ] L [ ] 交期： [ 8 ] 天

GKS002-A 10 - 240